



Cranberry Stained Glass, 102 Chain Lake Dr, Vantage Point 1A, Halifax, B3S1A7

Date	Kiln:	Firing Type: CAST	Glass info: COE 96
Segment	Rate (F degrees per hour)	To Temperature (F)	Hold Time
1	200	1225	40 min
2	600	1525	30 min
3	9999	960	60 min
4	200	500	15
5			
6			
7			
8			
Firing results and comments: DO NOT OPEN until kiln is at room temperature!!!			